

Test Report SL52105232811201TX Date:March 02,2021 Page 1 of 3

TAYA CANVAS(SHANGHAI)CO.,LTD

NO. 777 FENGGUAN ROAD, FENGJING INDUSTRIAL PARK, JINSHAN DISTRICT, SHANGHAI, CHINA.

The following sample(s) was/were submitted and identified on behalf of the client as:

Sample Description : (A)Sample

Sample Color : (A)White

Style No. : Butterfly Weldable

Proposed Care Instruction: -

Sample Receiving Date : Feb 25, 2021

Testing Period : Feb 25, 2021 - Mar 02, 2021

Test Result(s) : Unless otherwise stated the results shown in this test report refer only to the

sample(s) tested, for further details, please refer to the following page(s).

Test Performed : Selected test(s) as requested by applicant

Signed for and on behalf of SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd Testing Center

Hattie Chen (Account Executive)

lattice Chen



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms



Test Report

SL52105232811201TX

Page 2 of 3

Test Result

Fire Tests for Flame Propagation of Textiles and Films

(NFPA 701-2019; Method 1)

(A)

As Received

As Received											
Specimen	1	2	3	4	5	6	7	8	9	10	Average
Afterflame time(s)	NIL	3.0	NIL	2.0	NIL	NIL	2.0	3.0	NIL	NIL	1.0
The burning time of material that falls to the bottom of the chamber(s)	NIL	NIL	NIL	NIL	NIL	NIL	NIL	NIL	NIL	NIL	NIL
Flaming droplets or other flaming debris	N	Y	N	N	N	N	Y	Y	N	N	
									1		
Specimen	Weight (g)								Weight Loss (%)		
	Original (O)				After test (T)				(O-T)/O X 100		
1	21.6				20.8				3.7		
2	21.5				20.3				5.6		
3	21.5				21.0				2.3		
4	21.4				20.6				3.7		
5	21.6				20.9				3.2		
6	21.5				21.0				2.3		
7	21.5				20.4				5.1		
8	21.4				19.7				7.9		
9	21.6				20.2				6.5		
10	21.5				20.5				4.7		
Average									4.5		
Standards deviation									1.8		

Date:March 02,2021

Remark: Y: Yes N: No

Conditioning:

- The specimens were dried for at least 30 minutes at 105°C ± 3°C (220°F ± 5°F).

Requirements:

- 1. Fragments or residues of specimens that fall to the floor of the test chamber shall not continue to burn for more than an average of 2 seconds per specimen for the sample of 10 specimens.
- 2. The average weight loss of the 10 specimens in a sample shall be 40 percent or less.
- 3. No individual specimen's percent mass loss shall deviate more than 3 standard deviations from the mean for the 10 specimens.
- 4. When a retest is required, no individual specimen's percent mass loss in the second set of specimens shall deviate from the mean value by more than 3 standard deviations calculated for the second set.

Comment:

The submitted sample **complies** the requirement prescribed in Chapter 10 of NFPA 701-2019 in "As Received" states.



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3[™]Building,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐汇区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666 f (86-21) 64958763 f (86-21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com




Test Report

SL52105232811201TX

Date:March 02,2021

Page 3 of 3

Sample Photo



End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/en/Terms-and-Conditions/Terms

3rdBuilding,No.889,Yishan Road,Xuhui District Shanghai,China 200233 中国・上海・徐江区宜山路889号3号楼 邮编: 200233 t (86-21) 61402666 t (86-21) 61402666

f (86-21) 64958763 f (86-21) 64958763 www.sgsgroup.com.cn e sgs.china@sgs.com